

# Elastoval Storm Minerale

**Description** High performance SBS modified elastomeric bitumen membrane for roofing works.

This product is designed as top layer in single or multi layer systems, for both new roofing works and refurbishment works.

**CE** Single layer and multi layer waterproofing systems according with EN13707

**Field of use** Exposed not-accessible and technical roofs .

**Certifications and Agreements** CE marking - FPC certificate number 1370-CPR-0042

**Composition**  
**Top Surface:** Mineral slate or Granules  
**Back Surface:** Film  
**Reinforcement:** Polyester reinforced with fiber glass

**Method of application** Fully torch applied

<b>Dimension and packaging</b>	<b>Elastoval</b>	<b>SM</b>
Thickness (mm)		5,0
Weight (kg/m2)		6,0
Rolls (m)		1x8



Property	Test Method	Unit	Value	Tolerance
Lenght	EN 1848-1	m	8,0	-1%
Width	EN 1848-1	m	1,0	-1%
Thickness	EN 1849-1	mm	5,0	±0,2
Weight	EN 1849-1	Kg/m2	6,0	±10%
Tensile strength at max	EN 12 311-1	L x T (N/50mm)	1200/1000	-20%
Elongation at max	EN 12 311-1 1999	L x T (%)	50/50	-15
Nail tearing resistance	EN 12 310-1	L x T (N)	250 /250	-30%
Static load	EN 12 730	Kg	25	≥
Resistance to impact	EN 12691	mm	2000	≥
Flexibility at low temperature	EN 1109	(°C)	-25	≤
Flow resistance at elevated temperature	EN 1110	(°C)	100	≥
Dimensional stability	EN 1107-1	%	±0,3	≤
Mineral surface adhesion	EN 12039	%	30	≤
Hail resistance (soft substrate)	EN 13583	m/s	20	≥
Hail resistance (hard substrate)	EN 13583	m/s	60	≥
Watertightness	EN 1928-B	kPa	500	≥
Flexibility at low temperature after thermal ageing	EN1296 EN 1109	(°C)	-15	+15
Flow resistance at elevated Temperature after thermal ageing	EN1296 EN 1110	(°C)	90	-10
Reaction to fire	EN 13501-1	-	F	-
External fire performance	EN 13501-5	-	Froof	-

#### Storage

This product is packaged in rolls set up vertically on pallet or wooden box. It must be stored vertically under shelter, away from heat sources.

#### Modifications

Our company reserves the right to modify its composition as a result of technologic and experiments improvements. This product data sheet supersedes the previous edition, to obtain the updated technical data sheet, please contact our technical department.