

Elastogum Antiradice PLA

Description	High performance SBS modified bitumen membrane with antiroot agent for green roofs. This product is designed as top layer in a multi layer waterproofing systems for green roofs. This product is also approved for foundation waterproofing works.
--------------------	---

CE	Top layer in a multi layer waterproofing systems according with EN13707 for flat roofs. Layer for foundation waterproofing works according with EN13969.
-----------	--

Field of use	Green roofs and foundations.
---------------------	------------------------------

Certifications and Agreements	CE marking - FPC certificate number 1370-CPR-0042
--------------------------------------	---

Composition	Top Surface: Film Back Surface: Film Reinforcement: Polyester reinforced with fiber glass
--------------------	--

Method of application	Fully torch applied
------------------------------	---------------------

Dimension and packaging	Elastogum Antiradice	4PLA
	Thickness (mm)	4,0
	Weight (kg/m2)	-
	Rolls (m)	1x10

Property	Test Method	Unit	Value	Tolerance
Lenght	EN 1848-1	m	10	-1%
Width	EN 1848-1	m	1,0	-1%
Thickness	EN 1849-1	mm	4,0	±0,2
Weight	EN 1849-1	Kg/m2	NPD	±10%
Tensile strength at max	EN 12 311-1	L x T (N/50mm)	850/700	-20%
Elongation at max	EN 12 311-1 1999	L x T (%)	50/50	-15
Nail tearing resistance	EN 12 310-1	L x T (N)	200/200	-30%
Static load	EN 12 730	Kg	20	≥
Resistance to impact	EN 12691	mm	1000	≥
Joints Shear resistance	EN 12317-1	N / 50mm	700	-20%
Flexibility at low temperature	EN 1109	(°C)	-20	≤
Flow resistance at elevated temperature	EN 1110	(°C)	100	≥
Dimensional stability	EN 1107-1	%	±0,3	≤
Watertightness	EN 1928-B	kPa	60	≥
Vapour Transmission (μ)	EN 1931	-	20000	≥
Root resistance	EN 13948	-	Passa/Passed	
Reaction to fire	EN 13501-1	-	F	-
External fire performance	EN 13501-5	-	Froof	-

Storage

This product is packaged in rolls set up vertically on pallet or wooden box. It must be stored vertically under shelter, away from heat sources.

Modifications

Our company reserves the right to modify its composition as a result of technologic and experiments improvements. This product data sheet supersedes the previous edition, to obtain the updated technical data sheet, please contact our technical department.