Elastoflex PL



Description	High performance SBS modified elastomeric bitumen membrane for roofing and waterproofing works. This product is designed as base layer in multi layer waterproofing systems, for both new roofing works and refurbishment works. This product is also approved
CE	Base layer for multi-layer roofing systems according with EN13707 for flat roofs. Layer for foundation waterproofing works according with EN13969.
Field of use	Exposed not-accessible roofs, technical roofs exposed or under heavy protection. Foundations.
Certifications and Agreements	CE marking - FPC certificate number 1370-CPR-0042
Composition	**Top Surface**: Film **Back Surface**: Film **Reinforcement**: Polyester reinforced with fiber glass
Method of application	Fully torch applied

Dimension and packaging

Elastoflex	3PL	4PL	5PL
Thickness (mm)	-	-	-
Weight (kg/m2)	3,0	4,0	5,0
Rolls (m)	1X10	1X10	1X10

Property	Test Method	Unit	Value	Tollerance
Lenght	EN 1848-1	m	10	-1%
Width	EN 1848-1	m	1,0	-1%
Thickness	EN 1849-1	mm	NPD	±0,2
Weight	EN 1849-1	Kg/m2	3,0 / 4,0 / 5,0	±10%
Tensile strength at max	EN 12 311-1	L x T (N/50mm)	550/350	-20%
Elongation at max	EN 12 311-1	L x T (%)	35/35	-15
Nail tearing resistance	EN 12 310-1	L x T (N)	140/140	-30%
Static load	EN 12 730	Kg	10	≥
Resistance to impact	EN 12691	mm	800	≥
Joints Shear resistance	EN 12317-1	N / 50mm	500/350	-20%
Flexibility at low temperature	EN 1109	(°C)	-15	≤
Flow resistance at elevated temperature	EN 1110	(°C)	100	≥
Dimensional stability	EN 1107-1	%	±0,3	≤
Watertightness	EN 1928-B	kPa	60	≥
Vapour Transmission (μ)	EN 1931	-	20000	≥
Reaction to fire	EN 13501-1	-	F	-
External fire performance	EN 13501-5	-	Froof	-

Storage	This product is packaged in rolls set up vertically on pallet or wooden box. It must be stored vertically under shelter, away from heat sources.
Modifications	Our company reserves the right to modify its composition as a result of technologic and experiments improvements. This product data sheet supersedes the previous edition, to obtain the updated technical data sheet, please contact our technical department.